

Aliphatic resins:

Product	Softening point, °C	Color, YI	Melt viscosity (at 106°C), mPa.s	Wax cloud point, °C
Escorez 1102	97-105	70 max		
Escorez 1102F	97-104	70 max	2.000-3.300	
Escorez 1102RM	96-104	70 max	1.000-2.000	190 max
Escorez 1304	97-105	60 max		85 max
Escorez 1310LC	91-97	40 max		90 max
Escorez 1401	115-123	60 max		95 max

Aliphatic-aromatic resins:

Product	Softening point, °C	Color, YI	Melt viscosity (at 106°C), mPa.s	Wax cloud point, °C	Solution cloud point, °C
Escorez 2101	87-95	110 max		92 max	
Escorez 2105	88-101	110 max	2.700 max	170 max	
Escorez 2173	86-92	85 max			20 max
Escorez 2184	95-101	100 max			
Escorez 2203LC	89-96	40 max		105 max	
Escorez 2520	17-23	3 max (Gardner)			

Hydrogenated resins:

Product	Softening Point, °C	Initial color, YI	Aromaticity, %
Escorez 5040		2.2 max	
Escorez 5300	100-110	2.2 max	
Escorez 5320	120-130	2.2 max	
Escorez 5340	135-145	2.2 max	
Escorez 5380	80-90	2.2 max	
Escorez 5400	100-106	4.5 max	
Escorez 5415	115-121	4,5 max	
Escorez 5490	87-93	4.5 max	
Escorez 5600	100-106	4.5 max	8-11
Escorez 5615	115-121	4.5 max	8-11
Escorez 5690	87-93	4.5 max	9.5-12